CALIFORNIA Performance Coatings

Interior or Exterior

Skid-Grip® 100% Acrylic Anti-Slip Surface Coating

65XX

Product Description:

Skid-Grip is a 100% acrylic-textured pavement coating for use over asphalt or concrete surfaces, anywhere an extremely durable, skid resistant finish is desired.

Recommended Use:

Patios, Pool Decks, Tennis Courts, Basketball Courts, Driveways, Steps, Walkways, Ramps

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

New asphalt and new concrete surfaces must cure for at least 28 days prior to applying SKID-GRIP. The surface to be coated should be well drained, free of cracks, clean and free of all loose dirt, debris, grease and oil.

SKID-GRIP may be applied by brush, ¾ inch roller or squeegee. Stir contents thoroughly to insure even dispersion. The most effective method is to pour a 3-5 inch ribbon of SKID-GRIP, sufficient to cover the surface to be coated, then either brush, roll or squeegee over the entire surface.

Architectural Specifications:

2 coats Skid-Grip on properly prepared ashphalt, concrete or wood.

Precautions:

Do not apply when air and surface temperature are below 50°F (10° C). Do not apply when rain is imminent. Do not apply when surface is above 140°F (60° C). Do not apply over tar emulsions less than 4 years old.
Do not allow traffic over surface for at least 24 hours (or 48 hours in humid conditions). *Pool Decks must be clean and dry. Do not use 24 hours and/or after application.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

*Do not put in service until 24 hours after the last coat.

Product Specifications:

Type:	Acrylic Latex
Exposure:	Interior or Exterior
Specular Gloss:	<5 @ 60° ±5
Volume Solids:	67.2% ±2
Solids by Weight:	80.0 % ±2
Vehicle:	35.5 % ±2
Pigment:	64.5 %±2
Dry Film Thickness:	9 mils
Viscosity @ 77 °F:	85 KU ± 5
Maximum VOC:	100 g/liter
Flash Pt °F:	Non-combustible
Thinner:	Water
Clean Up:	Soap & Water

Available Colors and Bases:

7 Stock

Available Package Sizes:

Quart Gallon

(Weight Per Gallon: 13.8 lbs. ± .5 lb)

Drying Times:

To Touch:	N/A hrs.
To Handle:	48* hrs.
To Recoat:	N/A hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth:	N/A	s.f./gal.
Porous:	90-100	s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush -
Synthetic, Nylon or Polyester

Roller -
3/4" Nap Synthetic Fiber

Airless Spray -
.017 to .019 Tip

Squeegee